Proceedings of CONF-MCEE 2026 Symposium: Advances in Sustainable Aviation and Aerospace Vehicle Automation
DOI: 10.54254/2755-2721/2026.KA28784

Technical Comparative Analysis of Alumina-Based and Zeolite Catalysts to Dimethyl Ether Conversion

Hanbo Zhao

Faculty of Science and Engineering, University of Nottingham, Ningbo, China
ssyhz28@nottingham.edu.cn

Abstract: Dimethyl ether is one of the important components of new alternative energy sources that support sustainable development. Its clean and efficient characteristics make it applicable in various chemical industries such as fuels, etc. Among the generation processes, the indirect synthesis method is the mainstream synthesis method, and the core principle is the dehydration of methanol. The research on this production method mainly focuses on the reaction catalysts. However, these studies mostly focus on the experiments and analyses of a single technology and are insufficient in comparing and systematically organizing the methods. This paper employs literature review and case studies to compare the two most common types of catalysts for dimethyl ether production (alumina type and zeolite type) to determine their applicability at different temperatures and their stability under certain factors' influence. The analysis and conclusions in this paper may contribute to a more comprehensive understanding of the basis of dimethyl ether production and provide inspiration for more subsequent studies on catalysts and other aspects.

Keywords: Dimethyl ether (DME), Alumina-based Catalysts, Zeolite catalysts, Methanol, Catalytic Performance

1. Introduction

With the widespread adoption and implementation of the concept of sustainable development worldwide, the demand for energy structure transformation has become increasingly urgent. Clean, efficient, and renewable alternative energy sources have become one of the core contents of scientific research. Dimethyl ether (DME, C_2H_6O) is a highly anticipated alternative energy source. Its properties, such as safe storage and low pollution, make it an ideal substitute for diesel fuel. Moreover, DME can also replace chlorofluorocarbon as an environmentally friendly refrigerant and serve as an intermediate reactant in many chemical reactions. Generally, DME has a wide range of applications and a promising future. The preparation technology (methanol dehydration to produce DME) has become increasingly mature after a century of development [1]. The synthesis methods can be classified as direct synthesis and indirect synthesis. The former involves directly synthesizing DME from syngas, while the latter involves first producing methanol and then dehydrating it to obtain DME. Due to the relatively mature development of the indirect synthesis method, the research on improvement methods is mostly conducted based on this foundation.

© 2025 The Authors. This is an open access article distributed under the terms of the Creative Commons Attribution License 4.0 (https://creativecommons.org/licenses/by/4.0/).

DOI: 10.54254/2755-2721/2026.KA28784

However, research on methanol to DME conversion mostly focuses on individual technical analysis, lacking systematic organization and comparison. This paper will use literature review and comparative analysis method to compare the two most common catalytic technologies for the production of DME from methanol (alumina-based catalysis and zeolite catalysis). Through comparative analysis, it will help clarify the technical differences and applicable scenarios of the two catalytic reactions, providing theoretical guidance for research on DME production.

2. Literature review

The research for producing DME has lasted for nearly a hundred years. Currently, the studies of producing DME are continuing. Most of the research focuses on the development and analysis of new catalysts. For instance, during the research on Phosphorus-Containing Mesoporous Carbon Acid Catalyst, the activity selectivity and other properties of this special carbon material during the reaction were tested [2]. An analysis was conducted on the activity, selectivity, and stability of modified natural kaolin clay in the catalytic process, in order to confirm its catalytic performance [3]. Similarly, the catalytic performance of the modified alumina catalyst was analyzed [4]. In addition, numerous studies on the development or improvement of new catalysts have been carried out in recent years. Given the specificity of these studies, this article will focus on analyzing from the perspective of comparing common catalysts, which have been relatively neglected in these studies.

3. Technical principle

3.1. Analysis of the reaction mechanism of alumina-based catalysts




Figure 1. Reaction mechanism of γ-Al2O3-based catalysts [5]

As shown in figure 1, the catalyst adsorbs the methanol molecules. After that, through proton transfer and hydrogen bond interaction, a transition state complex with separated methoxy groups and new hydroxyl groups is formed, which can promote dehydration. Then, the second methanol molecule is adsorbed and dissociated, and finally, DME and the regenerated catalyst are produced.

DOI: 10.54254/2755-2721/2026.KA28784

3.2. Analysis of the reaction mechanism of zeolite-based catalysts




Figure 2. Reaction mechanism of zeolite-based catalysts [5]

As illustrated in figure 2, two viewpoints regarding the dehydration path of methanol adsorption on zeolite catalysts. One holds that the zeolite first adsorbs methanol molecules to form an intermediate product, and then, under the influence of methanol, this intermediate product generates another intermediate product, which subsequently undergoes dehydration to produce DME and returns to the catalyst. Another viewpoint considers that methanol is first adsorbed and dehydrated by the catalyst, and the resulting methoxy group then generates DME in the methanol vapor. Among them, the first route holds the dominant position [5].

4. Comparative analysis of catalytic performance of alumina-based and zeolite-based catalysts

4.1. Key catalytic properties and mechanism analysis

During the process of methanol dehydration to produce DME, both alumina-based and zeolite-based catalysts have shown excellent selectivity and other favorable characteristics, such as the resistance to high temperature and high pressure, strength of acidic sites, etc., making them suitable choices for the catalytic reaction [6,7]. However, there are many differences in their usage conditions.

4.1.1. Applicable temperature conditions

It is mentioned that the reaction temperature range for the alumina catalyst to catalyze the DME reaction is between 300 and 400℃, while the temperature range for the zeolite to act on the reaction is between 250 and 400℃ [6]. By comparison, the temperature range for catalyzing the production of DME by zeolites is wider, allowing them to function at relatively lower reaction temperatures. This makes zeolites more advantageous than alumina from the perspective of reaction temperature. This is because the dehydration of methanol to DME is essentially an exothermic reaction, and the thermodynamic equilibrium at high temperatures will limit production. In contrast, lower reaction temperatures are conducive to the forward reaction [8].

$$2CH_3OH \rightarrow CH_3OCH_3 + H_2O \qquad \Delta H = -23.4kJ \bullet mol^{-1} \tag{1}$$

DOI: 10.54254/2755-2721/2026.KA28784

Therefore, the low reaction temperature of zeolite is more compatible with DME production. ZSM - 5 can achieve a catalytic conversion rate (80%) equivalent to that of γ-Al2O3 at 320°C even at 230°C [9]. This also demonstrates the high efficiency of zeolite in catalysis at low temperatures, which is beneficial for controlling energy costs.

4.1.2. Comparison of water-induced deactivation

Apart from the high reaction temperature, the water absorption-induced deactivation is one of the main drawbacks of alumina catalysts [10]. The conversion rate of the feed curve of the methanol-water exhibits a significant decline over time, while the feed of pure methanol remains relatively stable [11]. This is because water competes with other reactants for active sites on the catalyst surface, thereby affecting the reaction.




Figure 3. Changes in methanol conversion rate with catalyst operating time (Triangle: Methanol-water mixture feed; Circle: Pure methanol feed)

In addition, similar experimental results can be found in Article [12]. After adding 23 Torr of water, the conversion rate of methanol decreased by more than ten percentage points. Meanwhile, in the presence of excessive water, the reaction temperature needs to be increased to achieve the normal conversion rate, and the upper limit of the conversion rate will also be restricted. For example, with 113 Torr excessive water, only a 39% conversion rate can be achieved at the optimal reaction temperature of 250°C, which is significantly lower than the 85% equilibrium conversion rate at the same temperature in Article [11]. All these factors indicate that water is a crucial factor affecting the stability of the alumina catalyst.

4.1.3. Catalyst deactivation

For zeolite catalysts, the deactivation caused by water is not as severe as that of alumina, indicating better water tolerance and more stable catalytic activity. Among the various catalysts used in the production of DMEs, it has been demonstrated that γ-Al_2O_3 is the most significantly affected by water molecules in blocking the active sites, while HZSM-5 is the least affected [7]. Experimental data show that with an equivalent quantity of water interference, the methanol conversion rate catalyzed by γ-Al_2O_3 declined by approximately 15% [12]. In contrast, the methanol conversion rate

DOI: 10.54254/2755-2721/2026.KA28784

catalyzed by HZSM-5 decreased by merely around 5%. This demonstrates the substantial difference in the tolerance to the impact of water between the two catalysts.

Although zeolite is less affected by water as alumina, it still has a shortcoming, specifically the formation of irrelevant hydrocarbons [13]. For zeolites, the presence of high-intensity acidic sites is beneficial for their catalytic activity at lower reaction temperatures. However, these strongly acidic sites may also lead to excessive reactions resulting in the formation of olefins and coking that block the pore structure, thereby causing the catalyst to lose its activity [7,14].

4.2. Summary

In contrast, zeolite catalysts exhibit lower water sensitivity and stronger resistance to water-induced deactivation. However, their strong acidic sites are prone to triggering side reactions. These reactions produce olefins, which not only compromise product purity but also cause coking that blocks the catalyst's pore structure. Alumina catalysts, by contrast, are highly susceptible to water. The presence of water leads to a substantial decline in methanol conversion rates. In conclusion, although both zeolite and alumina catalysts exhibit excellent properties such as high selectivity and conversion rate, making them common choices for catalyzing DME production, they are not without flaws. Each has its own drawbacks that must be addressed and improved upon.

5. Discussion

5.1. Challenges

The main challenges in developing DME production lie in increasing production. Driven by the pursuit of sustainable development goals and the mitigation of global warming, DME has been given urgent expectations in addressing the issue of replacing non-renewable energy sources such as oil and coal. By the middle of this century, proven oil reserves are expected to account for only 18%, and most of the fossil fuels are also facing a crisis of rapid depletion [14]. Therefore, as a new type of alternative energy with relatively more favorable production costs and environmental performance, increasing production is the most important task [15].

The key to increasing production lies in the improvement of the production method, specifically the development and optimization of catalysts. From the previous analysis, the main problems of the two commonly used catalysts nowadays are the influence of temperature on the catalyst's effectiveness, hydrophilic deactivation, and coke accumulation caused by irrelevant reactions. Therefore, the development challenge then becomes the development of highly stable catalysts with low water sensitivity, high product purity, and suitable reaction temperature.

5.2. Future directions

5.2.1. Indirect DME synthesis

Due to the urgent demand for DME production and the numerous challenges in improving the technology, the future development trend may lie in the following two directions. Firstly, the research and improvement of catalysts in the methanol dehydration process are needed, and reasonable solutions to overcome the deactivation problem should be sought. For example, by comparing the catalytic properties of synthesized KFI zeolite with those of two traditional catalysts, it was found that it has excellent activity and stability at low temperatures and low carbon formation, indicating that its catalytic performance is superior to that of traditional catalysts [16]. The

DOI: 10.54254/2755-2721/2026.KA28784

improvements in the indirect synthesis pathway mainly focus on the catalysts. The current research directions mainly involve metal doping modification, catalyst structure optimization, and the development of multifunctional catalysts.

5.2.2. Direct DME synthesis

Besides, in recent years, the direct synthesis pathway of DME has gradually attracted attention, becoming a research hotspot for some companies and researchers. It perhaps will become one of the future development trends [17]. The direct synthesis method is simple in process and has fewer thermodynamic restrictions, thus attracting attention. For example, in the research, it was proved that HSiW heteropoly acid was utilized for achieving the high yields in the direct synthesis method [17]. There are many similar studies on the direct synthesis method, which also reflects the recognition and expectation of researchers for its development. The development of catalysts and the exploration of direct synthesis methods are both continuously undergoing research, which open up unlimited possibilities for the production of DME.

6. Conclusion

This study compared the catalytic properties of two commonly used catalysts in the indirect synthesis method of methanol dehydration to DME, namely alumina and zeolite. The comparison involved temperature conditions and catalytic stability analysis, among other factors. Based on consideration of reaction heat and catalytic efficacy, it was concluded that zeolite is superior to alumina in terms of the required catalytic temperature due to its lower temperature. Moreover, the catalytic effect of alumina is severely hindered by water, resulting in a significant decrease in the conversion rate of methanol. In contrast, the impact of zeolite is not as significant. However, the irrelevant reactions caused by its strong acidity will reduce the product's purity, and the generation of coke will also damage its activity.

Given that this study mainly relies on literature analysis, and the analysis of data and phenomena is based on relevant reports, no specific experimental verification has been conducted. Therefore, there are some deficiencies in the data and phenomena in the actual situation. In future research, a series of comparative experiments can be designed and carried out to improve the accuracy and reliability of the data.

References

[1] Bakhtyari, A., & Rahimpour, M. R. (2018). Methanol to dimethyl ether. In Methanol (pp. 281-311). Elsevier.
[2] Valero-Romero, M. J., Calvo-Muñoz, E. M., Ruiz-Rosas, R., Rodriguez-Mirasol, J., & Cordero, T. (2019). Phosphorus-containing mesoporous carbon acid catalyst for methanol dehydration to dimethyl ether. Industrial & Engineering Chemistry Research, 58(10), 4042-4053.
[3] El-Aal, M. A., Said, A. E. A. A., Abdallah, M. H., & Goda, M. N. (2022). Modified natural kaolin clay as an active, selective, and stable catalyst for methanol dehydration to dimethyl ether. Scientific Reports, 12(1), 9407.
[4] Szczepanik, N., Kowalczyk, A., Piwowarska, Z., & Chmielarz, L. (2022). MCM-41-Type Mesoporous Silicas Modified with Alumina in the Role of Catalysts for Methanol to Dimethyl Ether Dehydration. Catalysts, 12(11), 1324.
[5] Khaleel, A., Ahmed, M. A., & Sowaid, S. B. (2019). Ti-doped γ-Al2O3 versus ZSM5 zeolites for methanol to dimethyl ether conversion: In-situ DRIFTS investigation of surface interactions and reaction mechanism. Colloids and Surfaces A: Physicochemical and Engineering Aspects, 571, 174-181.
[6] Azizi, Z., Rezaeimanesh, M., Tohidian, T., & Rahimpour, M. R. (2014). Dimethyl ether: A review of technologies and production challenges. Chemical Engineering and Processing: Process Intensification, 82, 150-172.

DOI: 10.54254/2755-2721/2026.KA28784

[7] Mondal, U., & Yadav, G. D. (2019). Perspective of dimethyl ether as fuel: Part I. Catalysis. Journal of CO2 Utilization, 32, 299-320.
[8] Ortega, C., Rezaei, M., Hessel, V., & Kolb, G. (2018). Methanol to dimethyl ether conversion over a ZSM-5 catalyst: Intrinsic kinetic study on an external recycle reactor. Chemical Engineering Journal, 347, 741-753.
[9] Chmielarz, L. (2024). Dehydration of Methanol to Dimethyl Ether—Current State and Perspectives. Catalysts, 14(5), 308.
[10] Mota, N., Millán Ordoñez, E., Pawelec, B., Fierro, J. L. G., & Navarro, R. M. (2021). Direct synthesis of dimethyl ether from CO2: Recent advances in bifunctional/hybrid catalytic systems. Catalysts, 11(4), 411.
[11] Raoof, F., Taghizadeh, M., Eliassi, A., & Yaripour, F. (2008). Effects of temperature and feed composition on catalytic dehydration of methanol to dimethyl ether over γ-alumina. Fuel, 87(13-14), 2967-2971.
[12] Xu, M., Lunsford, J. H., Goodman, D. W., & Bhattacharyya, A. (1997). Synthesis of dimethyl ether (DME) from methanol over solid-acid catalysts. Applied Catalysis A: General, 149(2), 289-301.
[13] Peinado, C., Liuzzi, D., Sluijter, S. N., Skorikova, G., Boon, J., Guffanti, S., ... & Rojas, S. (2024). Review and perspective: Next generation DME synthesis technologies for the energy transition. Chemical Engineering Journal, 479, 147494.
[14] Moghaddam, A. L., & Hazlett, M. J. (2023). Methanol dehydration catalysts in direct and indirect dimethyl ether (DME) production and the beneficial role of DME in energy supply and environmental pollution. Journal of Environmental Chemical Engineering, 11(3), 110307.
[15] Soltic, P., Hilfiker, T., Wright, Y., Hardy, G., Fröhlich, B., & Klein, D. (2024). The potential of dimethyl ether (DME) to meet current and future emissions standards in heavy-duty compression-ignition engines. Fuel, 355, 129357.
[16] Moghaddam, A. L., Ghavipour, M., Kopyscinski, J., & Hazlett, M. J. (2024). Methanol dehydration to dimethyl ether over KFI zeolites. Effect of template concentration and crystallization time on catalyst properties and activity. Applied catalysis A: general, 672, 119594.
[17] Peinado, C., Liuzzi, D., Boon, J., & Rojas, S. (2025). Improved productivity in direct dimethyl ether synthesis and sorption enhanced DME synthesis using tungstosilicic acid as the acidic function. Catalysis Today, 455, 115319.