Proceedings of CONF-MCEE 2026 Symposium: Geomaterials and Environmental Engineering
DOI: 10.54254/2755-2721/2026.MH30035

Application of Microscopic Characteristics of Nanosystems in Superconducting Technology and the Automotive Field

Qifeng Wang

School of AMSI, Imperial College, London, UK
qw1125@ic.ac.uk

Abstract. The rapid advancement of nanotechnology has revealed the significant potential of microscopic characteristics inherent in nanosystems for applications across various high-tech fields. This paper primarily investigates the microscopic properties of nanosystems, including surface and interface effects, small size effects, quantum confinement effects, and macroscopic quantum tunneling effects. It further explores the specific applications of these characteristics in superconducting technology and the automotive industry. The research aims to systematically analyze the role of nanoscale features in enhancing superconducting performance and their contributions to automotive lightweighting, energy efficiency, and intelligent sensing systems. The study concludes that nanostructures can effectively increase the critical current density and thermal stability of superconducting materials. Simultaneously, they play a pivotal role in developing lightweight composite materials and high-efficiency catalysts for vehicles. The findings of this paper provide a theoretical reference and practical guidance for the further development of interdisciplinary engineering applications of nanotechnology.

Keywords: nanosystems, microscopic characteristics, superconducting technology, automotive engineering, composite materials

1. Introduction

Nanotechnology, as one of the critical frontiers of 21st-century science, focuses on manipulating the physical and chemical behaviors of materials at the nanoscale, typically between 1 and 100 nanometers. Within this dimensional regime, nanosystems exhibit properties vastly different from their bulk counterparts due to a suite of unique microscopic characteristics. Phenomena such as surface and interface effects, small size effects, quantum confinement effects, and macroscopic quantum tunneling effects become dominant [1], fundamentally altering electrical, optical, magnetic, and mechanical properties. These unique properties have garnered widespread attention in high-technology sectors like superconducting technology and automotive engineering.

Superconducting technology, characterized by zero electrical resistance and perfect diamagnetism below a critical temperature, holds immense importance in energy transmission, high-field magnets for medical imaging (MRI), and advanced computing. However, widespread adoption is often limited by the performance of superconducting materials under practical operational conditions, such as high magnetic fields and elevated temperatures. Concurrently, the global automotive

© 2026 The Authors. This is an open access article distributed under the terms of the Creative Commons Attribution License 4.0 (https://creativecommons.org/licenses/by/4.0/).

DOI: 10.54254/2755-2721/2026.MH30035

industry faces pressing and multifaceted demands for lightweighting to improve fuel efficiency and reduce emissions, enhanced energy storage for electric vehicles, and the integration of intelligent systems for safety and autonomy. These challenges necessitate the development of novel materials with superior properties.

Although existing research has explored the application of nanomaterials in individual fields, a systematic analysis of the role of their microscopic characteristics at the intersection of superconductivity and automotive engineering remains relatively scarce. A comprehensive understanding of how nanoscale engineering can provide synergistic solutions to problems in these seemingly disparate fields is required. Therefore, this paper aims to systematically review the key microscopic properties of nanosystems and analyze their specific application mechanisms and effectiveness in both superconducting technology and the automotive sector. This research utilizes a combined methodology of literature review and case studies, integrating multidisciplinary research findings from materials science, condensed matter physics, and automotive engineering to reveal the potential of nanoscale properties in practical engineering applications. The study not only contributes to promoting the deep integration of nanotechnology in superconductivity and automotive fields but also provides a theoretical basis and technical pathway for subsequent related research, ultimately aiding in the transition towards more efficient and advanced technological ecosystems.

2. Key microscopic characteristics of nanosystems and their theoretical basis

2.1. Surface and interface effects

As material dimensions shrink to the nanoscale, the specific surface area increases dramatically. This results in a significant proportion of atoms—often exceeding 50% for particles below 10 nm—residing on the surface rather than in the bulk. These surface atoms possess unsaturated bonds and higher energy states compared to their bulk counterparts, leading to elevated surface energy and profoundly influencing the material's physical and chemical properties [2]. The unique properties of nanoparticles originate from changes in their atomic structure. Figure 1 quantitatively reveals that as the particle size decreases to the nanoscale, the proportion of atoms located at high-coordination sites such as corners and edges increases dramatically. These atoms possess higher reactivity, providing an atomic-level explanation for the high efficiency of nanocatalysts.




Figure 1. Distribution of surface atoms as a function of nanoparticle size

DOI: 10.54254/2755-2721/2026.MH30035

For instance, in nanocatalysts, this high surface activity and the abundance of active sites contribute to dramatically enhanced reaction efficiency and selectivity, a principle leveraged in automotive catalytic converters. Beyond catalysis, the increased surface area also critically affects interfacial interactions in composite materials. In polymer nanocomposites, for example, the immense interfacial area between nanofillers (like graphene or carbon nanotubes) and the polymer matrix governs stress transfer, ultimately determining the composite's mechanical strength, toughness, and barrier properties, which is crucial for applications like lightweight automotive panels.

2.2. Small size effect and quantum confinement effect

When the size of a material is reduced to a scale comparable to or smaller than the de Broglie wavelength of electrons, phonons, or excitons, its intrinsic properties begin to change. This phenomenon, known as the small size effect, can alter electrical conductivity, magnetic coercivity, and mechanical strength [3]. A particularly profound manifestation of this is the quantum confinement effect. In bulk semiconductors, electrons and holes are free to move, creating a continuous range of energy levels (bands). However, when the physical dimensions of the semiconductor are reduced to the nanoscale (as in quantum dots or nanowires), the charge carriers are spatially confined, leading to the discretization of energy levels. This size-dependent quantization allows for precise tuning of the bandgap; for example, cadmium selenide quantum dots can be engineered to emit specific colors of light simply by controlling their size. This characteristic is not only crucial for optoelectronics but also profoundly impacts the electronic properties of nanoscale superconducting structures and the operational principles of novel electronic devices.

2.3. Macroscopic quantum tunneling effect

The macroscopic quantum tunneling effect refers to the phenomenon where a macroscopic variable, such as the magnetic flux in a superconducting ring or the charge on a capacitor, undergoes a transition through a classically forbidden energy barrier due to quantum mechanical effects. This effect is negligible in macroscopic systems but becomes significant at the nanoscale, where the energy barriers are comparable to the quantum zero-point energy. The operational principle of key nanoscale devices hinges on the quantum mechanical behavior illustrated in Figure 2. Unlike classical particles, quantum particles can tunnel through energy barriers, enabling technologies ranging from single-electron transistors to superconducting junctions.




Figure 2. Conceptual illustration of the quantum tunneling phenomenon

It plays a crucial role in the operation of nanoscale electronic devices. In single-electron transistors, the tunneling of individual electrons through nanoscale junctions dictates the device's current-voltage characteristics. Furthermore, in superconducting systems, the tunneling of Cooper

DOI: 10.54254/2755-2721/2026.MH30035

pairs through thin insulating barriers forms the basis of Josephson junctions, which are the fundamental building blocks of Superconducting Quantum Interference Devices (SQUIDs)—the most sensitive magnetic field detectors known—and superconducting qubits for quantum computing [4]. The performance of these devices is exquisitely sensitive to the nanoscale geometry and composition of the tunneling barrier [5].

3. Application of nanoscopic characteristics in superconducting technology

3.1. Quantum effect regulation and enhancement of superconducting performance

A major challenge in applied superconductivity is the motion of magnetic flux vortices under an applied current, which generates electrical resistance and dissipates energy, even while the material remains in the superconducting state. The introduction of artificially engineered nanostructures, such as non-superconducting nanoparticles (e.g., $BaZrO_3$ in Yttrium Barium Copper Oxide-YBCO), nanorods, or intrinsic stacking faults, can effectively create a high density of pinning centers that immobilize these magnetic flux vortices [6]. The anisotropic layered structure of YBCO, detailed in Figure 3, dictates its superconducting properties. The CuO_2 planes serve as conduction channels, while the intervening layers allow for strategic incorporation of nanoscale flux-pinning centers to enhance current density.




Figure 3. Crystal structure of Yttrium Barium Copper Oxide ($YBa_2Cu_3O_{7-\delta}$, YBCO)

The interaction between the vortex core and these nanoscale defects is maximized when the defect size matches the coherence length of the superconductor, a condition readily achievable through nanoscale engineering. This targeted pinning leads to a substantial increase in the critical current density (Jc), the maximum current a superconductor can carry without loss, and enhances the thermal stability of superconducting materials by preventing catastrophic flux jumps. For instance, second-generation high-temperature superconducting (2G-HTS) tapes, which are characterized by their nanostructured YBCO layers, demonstrate critical current density (Jc) values an order of magnitude higher than their non-nanostructured counterparts [7]. This significant enhancement persists even under high magnetic fields, making these tapes highly suitable for demanding practical applications such as high-field magnets and efficient power cables.

3.2. Application of nanostructures in superconducting quantum devices

The field of superconducting quantum information technology is fundamentally reliant on nanofabrication. Superconducting qubits, such as transmon qubits, consist of circuit elements with

DOI: 10.54254/2755-2721/2026.MH30035

nanoscale Josephson junctions whose quantum state (the qubit) is defined by the tunneling of Cooper pairs. The fundamental shift from classical to quantum information processing is captured in Figure 4. A qubit's capacity for superposition, contrasting with a bit's binary state, enables the parallel computation paradigms that define quantum advantage.




Figure 4. Classical bit and superconducting qubit representation

The coherence time of these qubits—the duration for which quantum information is preserved—is critically dependent on minimizing losses, which are often associated with defects in the nanoscale oxide barrier of the junction or at interfaces. Similarly, SQUIDs, used for applications from biomagnetism to non-destructive evaluation, utilize one or two Josephson junctions whose dimensions and properties are controlled at the nanoscale. Advances in thin-film deposition, lithography, and etching allow for the precise definition of these junctions and superconducting loops, enabling the creation of devices that leverage quantum coherence and tunneling for unprecedented sensitivity and computational power. The ongoing improvement of these devices consistently involves pushing the limits of nanoscale materials engineering to create more perfect and stable interfaces and structures.

4. Application of nanoscopic characteristics in the automotive field

4.1. Lightweight and high-strength nanocomposites

The automotive industry's relentless drive towards improved fuel efficiency and reduced carbon emissions heavily relies on lightweighting. Replacing conventional steel components with those made from advanced nanocomposites offers a promising pathway. For instance, the addition of even small weight percentages (e.g., 0.5-2 wt%) of carbon nanotubes (CNTs) or graphene platelets to aluminum or magnesium alloys can lead to remarkable improvements in yield strength, tensile strength, and elastic modulus. This enhancement is primarily due to the Orowan strengthening mechanism (where nanoscale reinforcements impede dislocation motion) and effective load transfer from the matrix to the high-strength nanofillers via a strong interface [8]. Microstructural strengthening in nanocomposites is governed by dislocation-particle interactions. Figure 5 models the Orowan mechanism, showing how non-shearable nanoparticles force dislocations to bow and bypass, creating strengthening loops that impede plastic deformation.

DOI: 10.54254/2755-2721/2026.MH30035




Figure 5. Illustration of the Orowan strengthening mechanism

Polymer nanocomposites, such as polypropylene reinforced with nanoclay or CNTs, also see use in non-structural components like interior trim, dashboards, and body panels, reducing weight while improving dimensional stability and scratch resistance. The successful implementation of these materials, however, hinges on achieving uniform dispersion of the nanofillers and strong interfacial bonding, challenges that are active areas of materials research.

4.2. High-efficiency and environmentally friendly nanocatalysts and energy materials

Nanocatalysts are the active heart of modern three-way catalytic converters (TWCs) in gasoline-powered vehicles. The high surface-area-to-volume ratio of noble metal nanoparticles (typically platinum, palladium, and rhodium in the 2-10 nm range) dispersed on a high-surface-area alumina or ceria-zirconia support maximizes the number of active sites available for the simultaneous oxidation of carbon monoxide and unburned hydrocarbons and the reduction of nitrogen oxides [8]. The catalytic activity is so strongly size-dependent that the optimization of nanoparticle size and shape is a key focus for improving efficiency and reducing the usage of expensive precious metals. Emission control in modern automotive systems relies on the nanoscale architecture depicted in Figure 6. Noble metal nanoparticles dispersed on a high-surface-area support provide active sites for the simultaneous conversion of CO, HC, and NOx pollutants into benign gases.




Figure 6. Nanometer noble metal three-way catalyst for automotive exhaust purification

In the realm of energy storage for electric and hybrid vehicles, nanostructuring electrode materials in lithium-ion batteries is a key strategy to overcome kinetic limitations [9]. For example, silicon, which offers a theoretical capacity nearly ten times that of conventional graphite, suffers from massive volume expansion (>300%) during lithiation, leading to rapid failure. Structuring silicon into nanoparticles or nanowires can accommodate this strain, prevent pulverization, and

DOI: 10.54254/2755-2721/2026.MH30035

shorten lithium-ion diffusion paths, thereby enhancing cycle life and enabling faster charging capabilities.

4.3. Intelligent nanosensors and safety systems

The trend towards connected and autonomous vehicles creates a growing demand for robust, sensitive, and miniaturized sensors. Nanomaterials are ideally suited for this role. For instance, thin films containing CNTs or metal oxide nanoparticles (e.g., SnO_2, WO_3) exhibit changes in their electrical resistance upon exposure to specific gases (e.g., NOx, CO, H_2). These changes can be detected electronically, forming the basis for solid-state gas sensors that monitor cabin air quality or detect fuel leaks [10]. In tire pressure monitoring systems (TPMS), pressure-sensitive nanomaterials or nanoscale piezoelectric elements can offer higher sensitivity and lower power consumption than conventional sensors. Furthermore, nanoparticles such as quantum dots are being explored as fluorescent probes in optical sensors for engine oil condition monitoring, detecting wear metals or fuel dilution [11]. The integration of these diverse nanosensors into a vehicle's central electronic control unit (ECU) facilitates real-time health monitoring, predictive maintenance, and enhanced active safety systems, forming a critical sensory layer for the intelligent vehicle of the future.

5. Conclusion

This paper has systematically explored the application of microscopic characteristics of nanosystems in superconducting technology and the automotive field. The study concludes that surface effects, quantum confinement, and tunneling effects in nanomaterials play vital and distinct roles in enhancing superconducting performance and driving innovation in automotive engineering. Specifically, the strategic incorporation of nanostructures provides effective flux pinning to bolster the current-carrying capacity and thermal stability of superconductors. Concurrently, in the automotive sector, nanoscale reinforcements are pivotal for developing lightweight, high-strength composites, while nanocatalysts and nanostructured electrodes are essential for achieving stringent emission standards and high-performance energy storage. Nanosensors, leveraging their high sensitivity, further contribute to vehicle intelligence and safety.

However, this study has limitations, particularly in the detailed discussion of the scalable and cost-effective manufacturing of these advanced nanomaterials. The challenges of achieving perfect dispersion in composites, long-term stability of nanocatalysts under harsh conditions, and the reproducible fabrication of quantum devices at an industrial scale represent significant hurdles that were not deeply analyzed. Furthermore, the synergistic design principles that could allow a single nanomaterial system to function across different domains (e.g., a structural composite that also stores energy) were not explored. Future research should, therefore, focus not only on optimizing individual material properties but also on overcoming these manufacturing and integration challenges. Prospective studies may investigate novel bottom-up synthesis routes, advanced in-situ characterization techniques to understand degradation mechanisms, and multi-physics modeling to guide the design of next-generation nano-engineered components for both superconducting applications and the evolving automotive landscape, with a strong emphasis on sustainability and circular economy principles.

References

[1] Ma, D. J. Surface and Interface Effects of Nanomaterials [J]. Journal of Hebei Institute of Architectural Engineering, 1996(04): 37-42.

DOI: 10.54254/2755-2721/2026.MH30035

[2] Wang, S. X., & Zhang, Y. Z. Characteristics and Functions of Nanomaterials [J]. Jiangsu Ceramics, 2001(02): 5-6.
[3] Zhang, D. D., & Wang, Q. Q. Research on the Development Trends of Metallic Nanomaterials [J]. Sci-Tech Information Development & Economy, 2002(05): 89-92.
[4] Asha A B, Narain R. Nanomaterials properties [M]//Polymer science and nanotechnology. Elsevier, 2020: 343-359.
[5] Gatteschi D, Sessoli R. Quantum tunneling of magnetization and related phenomena in molecular materials [J]. Angewandte Chemie International Edition, 2003, 42(3): 268-297.
[6] Chen S Y, Chen I G, Hsieh P C, et al. Effect of nano-scale additions on the enhancement of superconductivity in Y-Ba-Cu-O materials [J]. Journal of electroceramics, 2004, 13(1): 857-863.
[7] Joyez P, Vion D, Götz M, et al. The Josephson effect in nanoscale tunnel junctions [J]. Journal of superconductivity, 1999, 12(6): 757-766.
[8] Zhang Z, Chen D L. Contribution of Orowan strengthening effect in particulate-reinforced metal matrix nanocomposites [J]. Materials Science and Engineering: A, 2008, 483: 148-152.
[9] Wang J, Chen H, Hu Z, et al. A review on the Pd-based three-way catalyst [J]. Catalysis Reviews, 2015, 57(1): 79-144.
[10] Chan C K, Peng H, Liu G, et al. High-performance lithium battery anodes using silicon nanowires [J]. Nature nanotechnology, 2008, 3(1): 31-35.
[11] Llobet E. Gas sensors using carbon nanomaterials: A review [J]. Sensors and Actuators B: Chemical, 2013, 179: 32-45.