Proceedings of CONF-MCEE 2026 Symposium: Geomaterials and Environmental Engineering
DOI: 10.54254/2755-2721/2026.MH31417

CO_2 Green Hydrogenation to Methanol and Process Design

Hongbin Huang

Beijing No.8 High School, Beijing, China
hongbin200808@163.com

Abstract. Human CO_2 emissions are an important driving factor in global warming, which is a threat to the Earth's climate system and ecosystems, with consequences such as increased average global temperature, frequent extreme heat waves, and ecosystem degradation. Nowadays, all CO_2 storage technologies still face a number of challenges, such as cost, capacity of treatment, and energy consumption. Among all Carbon Capture, Utilization, and Storage methods, hydrogenation of CO_2 into methanol (CH_3OH) has become one of the vital ways to deal with carbon dioxide, and at the same time, high-value chemicals and fuels were prepared. This article systematically reviews the catalytic systems adopted in the CO_2 hydrogenation to methanol process, mainly focusing on different catalyst types and giving an in-depth explanation of their reaction mechanisms. Meanwhile, a flow diagram was adopted to depict the integral process of this reaction under industrial conditions, involving key unit operations. The study shows that efficient catalysts and low-cost green hydrogen are the keys to the successful industrial application of this technology, and its extensive application will provide a good prospect for a green future.

Keywords: CO_2 Green Hydrogenation, Carbon Capture, Utilization, and Storage, Process Design

1. Introduction

At present, the concentration of CO_2 in the atmosphere has reached over 420 ppm and has greatly increased compared to preindustrial levels of about 280 ppm. The major cause of such a rapid increase in CO_2 concentration is considered to be large-scale combustion of fossil fuels. With a continuous imbalance in the global carbon cycle, the problem of controlling CO_2 emissions continues to become even more serious. Although CCS technology could temporarily store CO_2 in underground geological formations, this technology generally has disadvantages like high energy consumption, poor economic viability, and limitations in large-scale application. For instance, it takes around 0.3 to 0.6 MWh to capture one ton of CO_2, which is a month's quantity of electricity required for an average American household. The energy consumption of the direct air capture technology, which has to separate CO_2 from low-concentration gases, is even higher at 1.5 to 2.5 MWh per ton of CO_2 captured, which is economically not feasible.

By contrast, resource utilization, especially CO_2 hydrogenation to methanol, had been considered as a more sustainable solution. Methanol, a chemical raw material and energy carrier, can achieve a synthesis pathway using CO_2 as the carbon source while combined with hydrogen that is produced

© 2026 The Authors. This is an open access article distributed under the terms of the Creative Commons Attribution License 4.0 (https://creativecommons.org/licenses/by/4.0/).

DOI: 10.54254/2755-2721/2026.MH31417

from renewable energy by electrolysis of water. This review covers the catalytic mechanisms of the reaction, the industrial scalability potential, and the economic aspects of the Chemical Transport Model process in view of its important contribution to achieving the goals set by carbon neutrality.

2. CO_2 hydrogenation to methanol

2.1. Catalysts

Catalysts play a decisive role in CO_2 hydrogenation to methanol, and their performance directly influences the reaction's efficiency, product selectivity, and overall cost. Current research in this field has focused on three main kinds of catalysts: copper-based catalysts, precious metal catalysts, and oxide catalysts (Table 1). According to reaction activity, stability, and economic viability, different kinds of catalysts exhibit advantages and limitations.

Table 1. Comparison of main catalyst types for CO_2 hydrogenation to methanol

Catalyst Type	Example	Advantages	Disadvantages	Key Performance Metrics
Cu-Based	Cu	Low cost, moderate activity	Deactivation at high temperature, sintering	~25-30% conversion, ~50-70% selectivity
Noble Metal	Pd	High activity, considerate stability	Very high cost, limited resource	High conversion, selectivity
Oxide	ZrO	Excellent selectivity, high stability	Lower activity requires high pressure	>80% selectivity, lower conversion

And this type of catalyst has many advantages, such as low cost and high activity of the reaction. So it is the most mainstream choice in current industrial applications [1]. However, it suffers from copper particle sintering at temperatures higher than 300°C, resulting in a loss of catalytic activity [2]; meanwhile, Reserve Water Gas Shift decreases methanol selectivity. The typical performance is that the CO_2 conversion rate is around 25–30%, while the methanol selectivity is approximately 50–70% [1,2].

Beyond Cu-based systems, precious-metal catalysts (especially Pd-based catalysts) have been explored for CO_2 hydrogenation to methanol and can show strong activity and selectivity under relatively mild conditions. For example, a review reports that Pd and Pd-based bimetallic catalysts can achieve >10% CO_2 conversion with ~100% methanol selectivity at ≤30 bar and ≤250°C, outperforming Cu-based catalysts in that low-pressure/low-temperature window [3].

Nevertheless, their large-scale deployment is constrained by economics and supply risk. The annual average palladium price was about USD 980 per troy ounce in 2024 [4], illustrating the high raw-material cost exposure. In addition, platinum-group metals have notable supply concentration and trade dependence (e.g., the US net import reliance for platinum is reported as ~85%) [4], which further increases the risk and uncertainty for industrial-scale adoption.

In addition to precious-metal catalysts, oxide-based catalysts—especially In_2O_3–ZrO_2 systems—have attracted increasing attention for CO_2 hydrogenation to methanol because they can deliver very high methanol selectivity and good stability. For example, an In_2O_3/ZrO_2 catalyst achieved 94.39% methanol selectivity with 16.23% CO_2 conversion, and maintained performance over 100 h time-on-stream [5]. However, their overall activity is often moderate, so studies commonly operate at elevated pressures; for instance, Pt/In_2O_3 was tested at 5 MPa, where pure In_2O_3 under the same

DOI: 10.54254/2755-2721/2026.MH31417

conditions gave only 9.4% CO_2 conversion [6]. Overall, oxide catalysts are highly selective and stable, but frequently require higher-pressure operation to reach practical productivity [5,6].

Among these catalysts, $Cu/ZnO/Al_2O_3$ remains the industrial benchmark system in view of its excellent cost performance ratio in the hydrogenation of CO_2 to methanol. Behrens et al. pointed out that in $Cu/ZnO/Al_2O_3$ catalysts, copper sites serve as the main active centers for the reaction, and ZnO can stabilize the formate intermediate, which is crucial for methanol synthesis [7].

Most industrial methanol production still uses catalysts based on Cu ZnO Al_2O_3, and that goes back to the low-pressure method that ICI came up with in 1966, according to Ott and others in 2012. These catalysts work well in real operating conditions, like pressures in the tens of bars and temperatures around 200 to 300 degrees. They have high selectivity and can last a long time, which is why they are usually picked.

There is this example from Pontzen and colleagues in 2011, where they looked at CO_2-rich feeds using commercial Cu and ZnO catalyst pellets from Sud Chemie in a loop reactor setup with product separation and recycle. At 250 degrees C and 80 bar, for the CO_2 hydrogenation, they got a space time yield of 0.6 kg per liter cat per hour, and overall methanol selectivity was 63.9 percent from their pilot plant crude methanol analysis. It seems like this kind of pilot loop with a real commercial catalyst makes the data pretty relevant to industry, not just some small lab microreactor test.

ZnO does more than just act as a support in these systems. In practice, it helps guard against sulfur by scavenging those species, which protects the Cu sites from getting poisoned, as per Ott et al. in 2012. That part stands out because it shows how the components work together functionally.

2.2. Mechanism of reaction

Hydrogenation of CO_2 to methanol is a complex multistep reaction process with several reaction intermediates. It has been generally believed that, in copper-based catalyst systems, the reaction proceeds mainly through two pathways: a formate pathway and an RWGS reaction followed by CO hydrogenation pathways.

In the formate pathway, CO_2 firstly chemisorbed on the catalyst surface and then reacts with dissociative adsorbed hydrogen to produce formate (HCOO) intermediates. This intermediate further undergoes successive hydrogenation processes, sequentially converting to HCOOH, HCOH, and CH_3O, ultimately desorbing to form methanol. ZnO serves as a Lewis acid site to effectively stabilize the formate intermediate, enhancing reaction activity and improving selectivity. This mechanism has been confirmed in the studies of Kattel et al. [8] and Behrens et al. [7].

The other pathway is the RWGS reaction pathway, which initially occurs as: $CO_2 + H_2 \rightleftharpoons CO + H_2O$

Further hydrogenation of the resulting carbon monoxide takes place with formyl, formaldehyde, and methoxy as intermediates to form methanol. Suppression of the RWGS reaction holds the key to better methanol yield. In reality, RWGS will consume hydrogen to make CO and water, and the CO can desorb and leave as a by-product, therefore reducing overall methanol selectivity and carbon efficiency, especially at higher temperatures where RWGS is more favorable. Suppression of the RWGS reaction, according to a study by Bowker, holds the key to improved methanol yield [9].

Moreover, the interaction of metallic copper with the ZnO support is a crucial factor in catalytic activity. The ZnO not only stabilizes the dispersion of copper nanoparticles against sintering but also increases the activation capability of CO_2 on the copper surface. This synergistic effect of CuZnO is considered one of the core issues of current catalyst research.

DOI: 10.54254/2755-2721/2026.MH31417

2.3. Process design: from laboratory to industrialization




Figure 1. Real life BFD cycle of CO_2 hydrogenation to methanol reproduced [10]

The scaling up of this reaction, CO_2 hydrogenation to methanol from laboratory to industrial scale, demands systematic integration of unit operations, energy management, and economic considerations. A general industrial process for CO_2 to methanol could be divided into three main parts: raw material preparation, the reaction process, and product separation.

In the raw material preparation stage, CO_2 is captured and usually purified by amine absorption from industrial flue gases, while being compressed to 50–100 bar. Hydrogen is produced by water electrolysis driven by renewable electricity and has to be compressed, too. Then, hydrogen and CO_2 are mixed in a specific molar ratio, usually H_2:CO_2 ≈ 3:1, to drive the reaction toward methanol formation. Precise control of this ratio will be very important for improving conversion rates and reducing side reactions.

During the reaction stage, the mixed gases are preheated and passed through a multitubular fixed-bed reactor loaded with catalysts, such as $Cu/ZnO/Al_2O_3$. Given the strong exothermicity of the CO_2 hydrogenation reaction, heat transfer media (such as molten salt) are required to remove reaction heat in a timely manner in order to control the reaction temperature within an optimal window of 200–250°C. The gases at the reactor outlet comprise methanol, water, and unreacted CO_2 and H_2.

The reaction product, during the product separation stage, is first cooled through a condenser, then separated into crude methanol and water in a flash tank. The uncondensed gases, mainly CO_2 and H_2, are recycled back to the reactor to improve the atomic utilization efficiency of carbon and hydrogen. Finally, the crude methanol-water mixture is further purified through a distillation column to obtain a methanol product meeting the industrial standards.

3. Challenges and perspectives

3.1. Technical and economic challenges

Various challenges arise on pathways to massive-scale applications of CO_2 hydrogenation to methanol. Firstly, the $Cu/ZnO/Al_2O_3$ catalysts are susceptible to sintering deactivation at higher temperatures (>200°C), causing a decrease in active surface area, while the competing RWGS reaction reduces overall selectivity to methanol synthesis [7,8]. The economic feasibility of green

DOI: 10.54254/2755-2721/2026.MH31417

methanol largely depends on the cost of green hydrogen. At the current stage, hydrogen production by renewable energy electrolysis of water accounts for more than 60% of the total production cost. Although current costs remain high, future costs are likely to be considerably lower with advances in electrolyzed technologies including Proton Exchange Membrane and Solid Oxide Electrolyzer Cell and increasing renewable energy installed capacity. Besides, the whole process from capturing CO_2 to preparing hydrogen to high-pressure reaction has huge energy consumption. Therefore, efficient heat integration between exothermic processes (reactor) and endothermic processes (capture, electrolysis) is a key task in enhancement efforts toward overall energy efficiency.

3.2. Future directions of research

Future research on catalysts seems like it's heading toward making ones that really perform well. Like, building new high-performing ones. One direction that looks promising is In_2O_3-based catalysts. They have shown methanol selectivities above 80 percent. And they resist sintering, which helps them stay active longer. That part about staying active over time stands out.

Single-atom catalysts and dual-atom ones are getting more interest too. They combine efficiency with stability by maximizing the use of the metal and precisely controlling the active sites. It feels like that could be key to better results.

The commercial side of e-methanol relies a lot on green hydrogen being cheap. Except for the catalyst itself. As electrolyzers improve in efficiency and renewable power scales up, the cost of green hydrogen should fall quite a bit. Many analyses say that, especially from 2030 to 2040. I am not totally sure about the exact numbers, but it seems substantial.

Process design plays a role as well. Water comes out as a product in CO_2 hydrogenation. So removing it in situ pushes the equilibrium toward higher conversion in one pass. That reduces recycling rates and energy use overall. Process intensification approaches could help here. Such as enhanced absorption reactors and membrane reactors. They might be useful for that.

Policy can also change the economics. Like carbon pricing. For example, the European Unions Emissions Trading System. It internalizes the cost of CO_2 emissions, which makes green methanol more competitive. Some people think that will shift things a lot.

4. Conclusion

Hydrogenation of CO_2 to methanol is a very promising technological route for establishing closed carbon cycles and further developing a circular carbon economy. While copper-based catalysts and mature reactor designs form a ground for its industrialization, the commercial feasibility of the technology is still reliant on solving some key issues, such as catalyst stability, reduction of green hydrogen costs, and optimization of energy integration within the process. Together with substantial progress in catalyst design, process intensification, large-scale production of green hydrogen, and policies that support this direction, the CO_2-to-methanol technology will develop from experimental and demonstration stages into an important pillar of the sustainable chemical industry that transforms the global CO_2 emission problem into a valuable and utilizable resource.

References

[1] Pontzen, F., Liebner, W., Gronemann, V., Rothaemel, M. & Ahlers, B. (2011). CO_2-based methanol and DME—Efficient technologies for industrial scale production. Catalysis Today, 171, 242–250. doi: 10.1016/j.cattod.2011.04.049.

DOI: 10.54254/2755-2721/2026.MH31417

[2] Arena, F., Mezzatesta, G., Spadaro, L. & Trunfio, G. (2014). Latest Advances in the Catalytic Hydrogenation of Carbon Dioxide to Methanol/Dimethylether. In B. M. Bhanage & M. Arai (Eds.), Transformation and Utilization of Carbon Dioxide (pp. 103–130). Springer, Berlin, Heidelberg. doi: 10.1007/978-3-642-44988-8_5.

[3] Ojelade, O. A., & Zaman, S. F. (2020). A review on Pd based catalysts for CO_2 hydrogenation to methanol: In-depth activity and DRIFTS mechanistic study. Catalysis Surveys from Asia, 24, 11–37. https: //doi.org/10.1007/s10563-019-09287-z

[4] U.S. Geological Survey. (2025). Platinum-group metals (Palladium, platinum, iridium, osmium, rhodium, and ruthenium). In Mineral commodity summaries 2025 (pp. 136–137). U.S. Geological Survey.

[5] Zain, M. M., Mohammadi, M., Kamiuchi, N., & Mohamed, A. R. (2020). Development of highly selective In_2O_3/ZrO_2 catalyst for hydrogenation of CO_2 to methanol: An insight into the catalyst preparation method. Korean Journal of Chemical Engineering, 37, 1680–1689. https: //doi.org/10.1007/s11814-020-0573-7

[6] Sun, K., Rui, N., Zhang, Z., Sun, Z., Ge, Q., & Liu, C.-J. (2020). A highly active Pt/In_2O_3 catalyst for CO_2 hydrogenation to methanol with enhanced stability. Green Chemistry, 22(15), 5059–5066. https: //doi.org/10.1039/D0GC01597K

[7] Behrens, M., et al. (2012). The Active Site of Methanol Synthesis over $Cu/ZnO/Al_2O_3$ Industrial Catalysts. Science, 336(6083), 893–897.

[8] Wang, Y., Kattel, S., Gao, W., Li, K., Liu, P., Chen, J. G., & Wang, H. (2019). Exploring the ternary interactions in $Cu–ZnO–ZrO_2$ catalysts for efficient CO_2 hydrogenation to methanol. Nature Communications, 10, 1166. https: //doi.org/10.1038/s41467-019-09072-6

[9] Bowker, M. (2019). Methanol Synthesis from CO_2 Hydrogenation. ChemCatChem, 11(17), 4238–4246. https: //doi.org/10.1002/cctc.201900401

[10] Su, C., Wei, H., Wang, Z., Ayed, H., Mouldi, A., & Shayesteh, A. A. (2022). Economic accounting and high-tech strategy for sustainable production: A case study of methanol production from CO_2 hydrogenation. International Journal of Hydrogen Energy, 47(62), 25929–25944. https: //doi.org/10.1016/j.ijhydene.2022.01.124